

WKDT

Meshes & laid scrims

Product forms and specifications for material selection.

Technical catalogue
English edition / October 2026

Product forms, material composition and specification tables.


For grade selection, samples and current specifications, contact inquiry@weikongda.com.

Glass mesh & self-adhesive mesh



Weight (g/m ²)	Form / structure	Grid (mm)	Yarn size (tex)	Thread count (ends/cm)	Resin (%)
50	Self-adhesive	—	—	3.2	28
60±4	Mesh	—	Warp 66 Weft 80	Warp 3.54 Weft 3.54	—
60±4	Mesh	—	Warp 66 Weft 80	Warp 3.54 Weft 3.15	—
60	Self-adhesive	—	—	3.2	28
65	Self-adhesive	—	—	3.6	28
70	Self-adhesive	—	—	3.6	28
75	Self-adhesive	—	—	3.6	28
110	Self-adhesive	—	—	3.6	30
130±10	Mesh	4 × 4	Warp 200 Weft 300	Warp 2.5 Weft 2.5	—
160	Mesh / Coated mesh	5 × 5	—	—	—
250±8%	Mesh / AR mesh	8 × 8±8%	—	—	—

Glass & PET laid scrims



Weight (g/m ²)	Material	Grid (mm)	Yarn size (tex)	Tensile load (N/50mm)	Elongation (%)	Binder
3.8-4.2	PET	4 × 6	Warp 7.6 Weft 7.6	Warp 66 Weft 41	Warp 20 Weft 20	PVOH
4-5	PET	2.5 × 10	Warp 7.6 Weft 7.6	Warp 68 Weft 24	Warp 20 Weft 20	PVOH
4	PET	3 × 25 × 25	Warp 7.5 Weft 7.5	Warp 50 Weft 10	Warp 20 Weft 20	PVOH
5.5-6	PET	2.5 × 5	Warp 7.6 Weft 7.6	Warp 83 Weft 41	Warp 20 Weft 20	PVOH
6	Glass	12.5 × 12.5	Warp 34 Weft 34	Warp 130 Weft 130	<4	—
10	Glass	6.25 × 12.5	Warp 34 Weft 34	Warp 160 Weft 80	<4	—
10	Glass	10 × 10	Warp 34 Weft 34	Warp 150 Weft 150	<4	—
12	Glass	6.25 × 6.25	Warp 34 Weft 34	Warp 160 Weft 160	<4	—
15-16.5 / 15	Glass	5 × 5	34	Warp 120-150 Weft 250	Warp 4 Weft <4	PVOH
24	Glass	3 × 3	Warp 34 Weft 34	Warp 300 Weft 300	<4	—
27-30	Glass	3 × 3	Warp 34 Weft 34	Warp 250-300 Weft 250-300	Warp 4 Weft 4	PVOH
58	PET	4 × 4	Warp 55 Weft 55	Warp 600 Weft 600	Warp 20 Weft 20	Light PVC